


□ MASTERPROOF IWP - 1

Integral Waterproofing Liquid For Cement Concrete & Mortars



DESCRIPTION

MASTERPROOF IWP – 1 is a liquid integral waterproofing additive (Admixture) for cement concrete and mortar. The waterproofing constituent of the MASTERPROOF IWP – 1 does not dissolved in water in which it is added and remains hardened concrete as a permanent constituent. One of the constituent is water reducing agent which allows the reduction of water content of the concrete mix thus increasing the strength of the concrete while maintaining the workability. It does not alter the setting time of the concrete mortar.

FEATURES & ADVANTAGES

- Increases workability of the concrete mix.
- Reduces capillary action.
- Reduces vapour transmission through walls and slabs.
- Non-toxic.
- Does not corrode the reinforcement.
- Makes concrete waterlight.

TYPICAL APPLICATIONS

- Used in mass concrete
- Foundation walls.
- Floors
- Cement stucco
- Masonry mortars

TECHNICAL CHARACTERISTICS


- Nature : Single component, Liquid
- Colour : Light Bownish
- Specific Gravity at 30°C. : 1.150±0.020 gms/cc
- Consistency : Medium Viscous Liquid
- Compatibility : Compitable with all types of admixtures & can be used with all Portland cement grades.
- Air entertainment : Approximately 2% additional air over control concrete
- Cloride content : Nil, according to BS-5075 PART 1 & IS 6925

ENGINEERING DATA

Specification Complies : Product meets the Indian standard Specifications IS:2645-2003. And American Standard Testing Materials ASTM C – 494, Type A & D

▣ MASTERPROOF IWP - 1

Integral Waterproofing Liquid For Cement Concrete & Mortars



DIRECTION FOR USE

DOSAGE

Stir well the material before use.

Dose of 100 ml per 50kg. bag of cement is usually sufficient to produce waterlight concrete or mortar. Dose can be redesigned and tested by normal trial batch methods.

Add Masterproof IWP – 1 to the mixing (gauging) water. Water content should be reduced accordingly to achieve the most effective waterproofing and strength of the concrete / mortar.

CLEANING OF TOOLS & EQUIPMENTS

Tools and Equipments can be cleaned with water.

STORAGE AND SHELF LIFE

Store the material at a cool & dry place (at 25°C. temp. & 50% RH). Shelf life is two years.

PACKING

100ml, 1 liter, 5 liters, 20 liters, 200 liters

PRECAUTIONS

- Do not mix with dry cement
- Add to mixing (gauging) water