ShaliUrethane® BTD



Water Based UV Resistant Elastomeric PU Liquid Membrane

Description

ShaliUrethane® **BTD** is high performance, water based, cold applied, single component elastomeric in-situ liquid membrane for waterproofing usually produced in White / Terracotta / Green color. It may also be supplied in Black color against specific orders.

ShaliUrethane[®] **BTD** is UV resistant. However, for better UV resistance, we recommend use of White colour BTD, having SRI Index > 109, thus facilitating considerable saving in energy.

ShaliUrethane® BTD forms a seamless monolithic membrane and can be applied on moist surface.

It conforms to ASTM C 836 and ASTM D 6083-97a.

Use Horizontal / Vertical grade of **ShaliUrethane® BTD** for horizontal / vertical application respectively.

Characteristics - Physical

Color	White /	Touch Drying time #, minutes	20 - 30
	Terracotta /	Full cure time #, days	7
	Green	UV stability	Excellent
Solid content, %	> 80	VOC Content, gm / kg	Nil
Service temp, range, ^o C	- 20 to + 100	pH	Alkaline
Theoretical Coverage *, DFT, Kg / m² • For 1.0 mm • For 1.2 mm	1.85 2.20	Solar Reflective Index (ASTM C 1549, C 1371, E 1890) Terracotta / Green White	N/A 109
		Specific gravity @ 30 °C	1.5 ± 0.03
Application Temperature, ^o C	> 5	Elastic Recovery @ 150%	70 – 75
Viscosity @ 30 °C, cps	6500 ± 1500	elongation, %	

^{*} Depending upon surface condition

Characteristics - Technical

Elongation, %	ASTM D 2370	400 ± 50
Tensile strength, MPa	ASTM D 2370	1.40 ± 0.2
Adhesion to primed concrete, Pull off strength, MPa	ASTM D 4541	0.40
Extension after heat aging, mm	ASTM C 836	6
Crack bridging at low temperature	ASTM C 836	No cracking
Water Absorption %	IS 13826 Part 3	< 5
Hardness Shore A	ASTM D 2240	> 50

Application

- Roof / Terraces, including corrugated roof.
- Podium.
- Refurbishment of APP / SBS / TarFelt roof.
- · Gutter waterproofing.

[#] Depends up on weather condition.

Advantages

- White **ShaliUrethane**® **BTD** has excellent SRI of 109, thus facilitates energy saving and provides good cooling effect under the treated surface.
- White **ShaliUrethane**® **BTD** is recommended for all slope roofs and not trafficable roofs, which needs no protection.
- Can be applied on moist surface also.
- Excellent water vapour barrier.
- · High Crack Bridging.
- Monolithic / seamless / breathable in-situ Membrane.
- Excellent adhesion to concrete.
- Excellent elongation and very good low temperature flexibility.

Application Methodology

Surface Preparation

- Remove all loose gravel, dirt, oil, grease and foreign matter by jet of dry air and clean the surface mechanically or by grinding to make it smooth before application.
- Repair all cracks by cutting "V" groove and fill with PMC mortar prepared in the ratio of ShaliCrete: Cement: Sand (1:2:5).
- Provide 75 mm x 75 mm coving made out of PMC mortar as above, using ShaliSBR Latex as bond coat.
- Ensure gradient of 1: 100 towards drain by laying PCC admixed with integral waterproofing compound, ShaliPlast LW+ @ 200 ml / bag of cement preferably with galvanised chicken wire mesh.
- Ensure that there is no standing water on the applicable surface.

Material Preparation

- Stir ShaliUrethane® BTD by a slow speed mixture fitted with a suitable mixing paddle to
 ensure a homogenous mix. Small settlement is to be mixed by hand stirring first before
 mechanical stirring.
- After stirring, wait for the product to settle in order to let entrapped air escape.

Waterproofing Application

- Slightly damp the surface. Avoid standing water / ponding.
- Prime the surface
 - In case anti-root property is desired, use ShaliPrime WP WB @ 200 grm / m² or
 - In other case dilute ShaliUrethane® BTD with water @ 1:1 ratio and use as primer @ 400 gm /².
- Allow the primer coat to touch dry condition.
- Apply 1st coat of **ShaliUrethane BTD** @ 1 Kg / m² by brush / roller / airless spray while the primed surface is tacky. For faster and smoother application, apply with airless gun.
- Spread non-woven geo-textile or Fibre Glass Tissue / scrimp of 45 gsm with overlaps of 50
 mm in both directions when the surface is still tacky; this is optional, to be assessed as per
 site requirements to achieve higher mechanical properties.
- Allow 1st coat to dry for 10 12 hr.
- Apply 2nd coat of ShaliUrethane® BTD @ 1 kg / m² by brush / roller / airless spray for final DFT of 1500 micron in two coats.
- Ensure final curing time of 36 hrs before allowing / carrying out any further work.
- Extend waterproofing treatment up to 200 mm and terminate into groove on the parapet wall. Fill the groove with PMC mortar with ShaliSBR Latex.
- In case of vertical application, protect the applied liquid membrane
 - By sprinkling sand @ 200 grm / m² over the final coating when the surface is still tacky to facilitate plastering with 25 mm plaster admixed with ShaliPlast LW + @ 200 ml / bag of cement
- In case of horizontal surface, if protection is desired, protect the applied BTD
 - Preferably with ShaliProtek PU HA, high abrasion resistance liquid coating which can take foot traffic, or
 - Spread separation layer of 200 gsm geo-textile, ShaliGeoText 200, with overlap of 50

mm in both directions on fully cured waterproofed surface before laying protection screed, and then lay 50 mm plaster admixed with ShaliPlast LW + @ 200 ml / bag of cement.

- For Heavy duty area, apply third coat of ShaliUrethane® BTD @ 1 kg / m².
- Conduct ponding test after 7 days of curing at ambient temperature.

Precautions

- Mixing water is to be done for primer application @ 1:1 dilution
- In case of any application difficulty, seek assistance from STP's Technical Cell.
- Do not allow any movement over waterproofed area unless ponding is done and waterproofed area is protected as above.
- For metal roof contact STP's Technical Team for DTM Type primer.
- On unprotected surface of coating, do not allow standing water for longer time.

Health & Safety

- Avoid contact with skin / eyes and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapor.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 25 kg pack.

Storage

Store in a cool dry place, under shed, away from heat.

Shelf Life

12 months in original unopened sealed condition.





Product Range

Waterproofing & Insulation
 Road Surfacing
 Sealants & Adhesives
 Pipeline Coatings
 Protective/Anti-Corrosion Coatings
 Epoxy and Flooring
 Grouts and Admixtures (GARA)

■RestoFix - Repair/Rehabilitation ■Other Construction Chemicals



Advisory Cell: +91 81302 81114

www.stpltd.com