



Paveseal SB Clear

ACRYLIC SLIP RESISTANT SURFACE SEALER AND HARDENER



DESCRIPTION

Bostik Paveseal SB Clear is an acrylic slip resistance surface coating, sealer and hardener for concrete and masonry surfaces. It is a high performance solvent based acrylic coating for a protective and decorative coating for concrete and masonry. Specially formulated to reduce slip. Suitable for use on all types of structures whether they are new or old, providing a waterproof clear gloss finish, hard wearing and durable. It provides a tough layer to a variety of surfaces

RECOMMENDED USES

Suitable for use on bricks, clay pavers, pattern paving, concrete, masonry, pebble finishes, sandstone, slate, unglazed tiles and primed metal surfaces free of dust. Reduces slip on areas such as bathrooms, kitchen and laundry floors, foyers, patios, steps, and verandahs, courtyards, driveways, paths, fiberglass boat decks & industrial flooring.

FEATURES & BENEFITS

- Rapid drying surface coating for commercial/domestic and interior and exterior applications.
- Provides optimum adhesions, durability and enhanced surface grip.
- Protects surfaces from the spillage of food, grease & oil.
- Excellent UV and weather resistance.
- Excellent resistance to yellowing.
- Carbonation coating, low carbonation permeation.

- Prevents moisture ingress
- Protects concrete against acids and algae.

APPLICATION PROCEDURE

All surfaces should be dry and free from contamination such as oil, grease, loose particles, decayed matter, moss algae growth, laitance and all traces of mould release oils and curing compounds. This is best achieved by lightly grit-blasting the surface, high pressure water blasting is also effective in removing contamination.

Moss and Mould – Treat with household bleach. Allow 2-3 hours. Scrub and rinse thoroughly with clean water. Allow to dry.

Concrete – Allow new concrete to cure for 28 days. All concrete surfaces must be etched to achieve good adhesion. After etching wash the surface thoroughly with water and allow to dry. It is essential to protect an unbroken coating of Paveseal SB To ensure this is achieved, surfaces containing blow-holes or similar areas of pitting should first be filled using Bostik a cementitious fairing coat and this should be allowed to cure for approximately 48 hours dependent on ambient conditions before the application of Paveseal SB. The surface must be dry and moisture free prior to application of Paveseal SB.

Any areas of glass should be masked. Plants, grass,

joint sealants, asphalt and bitumen painted areas should be protected during application

MIXING

No mixing required, use straight from the container.

DO NOT DILUTE WITH SOLVENTS

PLACING

Paveseal SB may be applied using a brush, roller or spray application. All surfaces should be treated with two coats of Paveseal SB and applied until a uniform continuous coating is achieved with a minimum coverage rate of 5 sqm per litre per coat. Second and subsequent coats may be applied after 2 hours, at 20°C, after the first coat has dried. Paveseal SB may be over coated the following day, however ensure the surface is clean & free from contamination, any dust or foreign matter on the surface will effect the ultimate bond between coats.

CLEAN-UP

Wash equipment and clean up incurred material immediately using Solvent . Do not use solvents on skin. Cured Paveseal SB is difficult to remove via chemical means and mechanical means may be necessary.

PACKAGING

Bostik Paveseal SB is supplied in 1, 5 & 20 L

STORAGE & SHELF LIFE

Bostik Paveseal SB has a shelf life of 12 months when stored in unopened original containers, at temperatures between 4°C and 35°C. Freezing or prolonged exposure to direct heat or direct sunlight must also be avoided. Storage outside these guidelines may impair shelf life.

HEALTH & SAFETY

Avoid contact with skin and eyes. Wear protective gloves when applying product. If contact with skin occurs, wash with copious amounts of water. If contact with eyes occurs, flush with copious amounts of water ensuring eyes are irrigated for at least 15 minutes. If ingested, do not induce vomiting. Give plenty of water to drink. Consult doctor.

FIRE

Paveseal SB Textured is Flammable.



BOSTIK HOTLINE

Smart help +91 80 27833520

Bostik India Private Limited

124 / 1 & 124 / 2A, Kachanayakanahalli, Off. Hosur Road,
Bommasandra Post, Anekal Taluk, Bengaluru – 560 099, India.
E-mail : bostikinfo.india@bostik.com
For more information explore : www.bostik.com



Disclaimer : All representations & recommendations set forth are given in good faith & to the best of our knowledge. However, due to varying conditions & applications, the buyer shall conduct its own tests of this product before use. Under no circumstances will the manufacturer be liable for any loss, damage caused by incorrect usages. The sale of this product shall be on terms & conditions set forth on Bostik's order acknowledgement.