

Boscocem SBR

SBR LATEX EMULSION ADDITIVE





DESCRIPTION

Boscocem SBR is a styrene butadiene rubber latex emulsion additive. It is designed for use as an integral bonding agent with cement-based products in slurry bonding coats, mortars, screeds, renders and tile adhesives. It is used to improve adhesion to properly prepared substrates. The tile adhesive so prepared is good for bonding all types of tiles.

RECOMMENDED USES

Cement based toppings, patching mortars, leveling compounds and terrazzo, Waterproofing cement/sand renders / screeds, Bonding concrete repair mortars, Bonding agent for ceramic tiles, bricks, etc., Preparation of spatter dash

FEATURES & BENEFITS

Increases flexural and tensile strength, Improves bond strength, Improves workability, Improves abrasion resistance, Reduces shrinkage and cracking, Resists chemical and water resistance, Protects from freezethaw damage, Reduces water absorption of mortar

| PERFORMANCE PROPERTIES | |
|---------------------------|--------|
| Colour | White |
| emulsion Specific Gravity | 1.02 |
| рН | 7.8-10 |

APPLICATION PROCEDURE Surface Preparation

Surface must be structurally sound. Remove all deteriorated concrete, dirt, oil, grease, curing compounds, coatings and all bond-inhibiting materials from surface. New concrete and masonry surfaces must be cured 28 days. Preparation work should be done by high-pressure water blast, or other appropriate mechanical means to obtain a clean, exposed aggregate surface. Saturate surface with clean water. Substrate should be saturated surface dry with no standing water during application. Follow the surface preparation directions for the product in which Boscocem SBR is being used as an admixture.

Mixing

Bonding slurry: A mixture of 1:1. Boscocem SBR: OPC (by volume) bonding slurry is prepared and mixed in a clean container until a creamy brush consistency is obtained. Mix only the amount that can be used within the working life of the product.

Polymer admixture for mortars: With mixer running, add measured quantity of Boscocem SBR, water, OPC, sand and aggregate depending on type of application (refer to the following mix designs for batching proportions). Mix to desired consistency.

Typical designs are detailed below:

1. Render (Recommended thickness: 6mm to 8mm)

| | By Weight | By Volume |
|----------|-----------|-------------------------|
| Cement | 50 kgs | 1part |
| Sand | 125 kgs | 2 parts |
| Mortafix | 9 kgs | 1:1Boscocem SBR / water |
| Water | 9 kgs | to working consistency |
| | | |

Approximate Yield: 0.08m3

2. Heavy Duty Floor Screed

(Recommended thickness: 25mm to 40mm)

| | By Weight | By Volume |
|---------------|-----------|-------------------------|
| Cement | 50 kgs | 1 part |
| Sand | 75 kgs | 1.25 parts |
| Granite chips | 75 kgs | 1.25 parts |
| Mortafix | 9 kgs | 1:1Boscocem SBR / water |
| Water | 10 kgs | to working consistency |

Approximate Yield: 0.08m3

APPLICATION PROCEDURE

Bonding fresh mortar or concrete to hardened concrete: The properly prepared surface must be damp but free of standing water or puddles. Scrub bonding slurry thoroughly onto prepared substrate. Be sure entire surface and edges are coated. Apply mortar or concrete while bonding slurry is soft and plastic.

Polymer modified mortars: Must be placed immediately following bonding slurry. Trowel immediately and broom finish, if needed. Avoid over toweling or over finishing surface. It is impossible to achieve a hard steel trowel finish Boscocem SBR is normally self-curing. In hot weather or windy conditions, as soon as possible, the use of polyethylene sheeting is recommended for a minimum 24 hours.

CURING

Applications are cement based and in common with all such materials, must be cured in accordance with good concrete practice. The use of polythene sheeting is recommended for a minimum 7 days to prevent rapid drying out. Alternatively a Bostik curing aid can be used (see appropriate technical data sheet).

Cleanup

Wash all equipment in water or water/detergent immediately on completion of application and mixing. Clean drips, spills and smears while mix is still wet. Mixes containing Boscocem SBR are extremely difficult to remove if allowed to dry before cleaning.

PACKAGING

Available in 1, 5, 20, 20 and 200 Liter Drums.

STORAGE & SHELF LIFE

Boscocem SBR has a shelf life of 12 months from date of manufacture when kept in a dry store in the original, unopened. Material shall be stored under cover in a manner that will prevent damage preferable on pallets and protected from excessive heat and moisture, Do not freeze

HEALTH & SAFETY

Skin contact may cause moderate irritation & dermatitis, Eye contact may cause severe irritation and redness. Extensive inhalation of vapours may cause irritation to the throat, lungs, skin, & nose; nausea and headache. Ingestion may cause irritation to the mouth & stomach. For skin contact, remove & launder contaminated clothing. Wash thoroughly with soap & water. If irritation persists, call a physician. For eye contact, flush with water for 15 minutes. Call a physician. For inhalation, remove victim to fresh air. Call a physician.

FIRE

Product is non-flammable and poses no fire risk.

WARRANTY

Whilst Bositk India (P) Ltd., strives to ensure that any advice, information or recommendation given are appropriate and correct, it cannot accept any liability directly or indirectly arising out of the use of the product, since the method and place of application of the products are beyond their control. Its guarantee is therefore limited to the quality of materials delivered.

BOSTIK HOTLINE

Smart help +91 80 27833520

Bostik India Private Limited

124 / 1 & 124 / 2A, Kachanayakanahalli, Off. Hosur Road, Bommasandra Post, Anekal Taluk, Bengaluru – 560 099, India. E-mail: bostikinfo.india@bostik.com For more information explore: www.bostik.com